



Test of Bowling Lane

Type of Lane:

Synthetic
 Wood

Submitted by:

VPS EC

Date:

8/19/10

Description

Trade Name:

Fasttrack II

Permit No.:

FSZ-020

Sward Hardness

	<u>Average</u>	<u>Min</u>	<u>Pass/Fail</u>
Panel 1	49.33	35	PASS
Panel 2	51.11	35	PASS
Panel 3	#DIV/0!	35	#DIV/0!
Panel 4	#DIV/0!	35	#DIV/0!

Coefficient of Friction

	<u>Average</u>	<u>Max</u>	<u>Pass/Fail</u>
Panel 1	0.114	0.29	PASS
Panel 2	0.112	0.29	PASS
Panel 3	#DIV/0!	0.29	#DIV/0!
Panel 4	#DIV/0!	0.29	#DIV/0!

All measurements below are for information purposes only

Surface Roughness

Panel 1	13.30
Panel 2	13.36
Panel 3	#DIV/0!
Panel 4	#DIV/0!

Panel Thickness

Panel 1	0.405
Panel 2	0.406
Panel 3	#DIV/0!
Panel 4	#DIV/0!

Durometer

Panel 1	92.39
Panel 2	92.38
Panel 3	#DIV/0!
Panel 4	#DIV/0!

